

Material: SAE Alclad 6061

Standard Specification For Aluminium Alloy

Group: Non-Ferrous Aluminium Alloys

Sub Group: SAE Alclad 6061 Aluminium Alloy

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Plate and Sheet

Chemical Composition			Heat Treatment	
Silicon	Si %	0.400 - 0.800	As Raw or Temper or Solution Treated or Aging	
Chromium	Cr %	0.040 - 0.350		
Manganese	Mn %	0.150 max.		
Magnesium	Mg %	0.800 - 1.200		
Copper	Cu %	0.150 - 0.400		
Iron	Fe %	0.700 max.		
Zinc	Zn %	0.250 max.		
Titanium	Ti %	0.150 max.		
Other	Ot %	1.000 max.		
Aluminium	Al %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	138 min.
-	-	-	Yield Strength in Mpa	82.7 min.
-	-	-	Elongation in %	6 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
6061	SAE	USA	Bar, Rod, Shapes, Tube and Wire, Extrusion
6061	AS	Australia	Plate, Sheet, Rod, Bar, Wire and Strip
F901 6061	ASTM	USA	Bolt and Nut
SB-210 6061	ASME	USA	Tube
A05050	UNS	USA	Casting
A 6061S	JIS	Japan	Bar, Rod, Shapes, Tube and Wire, Extrusion
AL-P6061	UNI	Italy	Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com