

Material: SAE D550

Standard Specification For Ductile Cast Irons Castings

Group: Ferrous SG Iron I Ductile Iron Alloys

Sub Group: SAE D550 Ductile Cast Irons Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	3.200 - 4.100	As-Cast	
Silicon	Si %	1.800 - 3.000		
Manganese	Mn %	0.100 - 1.000		
Phosphorus	P %	0.050 max.		
Sulphur	S %	0.035 max.		
Magnesium	Mg %	0.025 - 0.060		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 550 min. Yield Strength in Mpa 350 min. Elongation in % 4 min. Reduction of Area in % - Hardness in BHN 217 - 269 Impact in Joule 40 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
JS 550-5	ISO	International	Casting
JS 550-5	AS	Australia	Casting
A 536 80-55-06	ASTM	USA	Casting
D5504	SAE	USA	Casting
FCD 600-3	JIS	Japan	Casting
EN-JS1092	UNI	Italy	Casting
JS 550-5 C	ISO	International	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com