

Material: SAE D7003

Standard Specification For Ductile Cast Irons Castings

Group: Ferrous SG Iron / Ductile Iron Alloys

Sub Group: SAE D7003 Ductile Cast Irons Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	3.200 - 4.100	As-Cast	
Silicon	Si %	1.800 - 3.000		
Manganese	Mn %	0.100 - 1.000		
Phosphorus	P %	0.050 max.		
Sulphur	S %	0.035 max.		
Magnesium	Mg %	0.025 - 0.060		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 700 min. Yield Strength in Mpa 425 min. Elongation in % 3 min. Reduction of Area in % - Hardness in BHN 241 - 302 Impact in Joule 27 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
JS 700-2	ISO	International	Casting
JS 700-2	AS	Australia	Casting
A 536 100-70-03	ASTM	USA	Casting
D700	SAE	USA	Casting
EN-GJS-700-2	UNE	Spain	Casting
EN-GJS-700-2	SS	Sweden	Casting
5.3300	EN	European Union	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com