

## Material: SAE J403 | SAE J1397 UNS G10200 - Cold Drawn Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing

**Group:** Ferrous Mild Steel Alloys

**Sub Group:** SAE J403 | SAE J1397 UNS G10200 - Cold Drawn Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.180 - 0.230	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.300 - 0.600		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-	<b>Mechanical Properties</b> Tensile Strength in Mpa 420 min. Yield Strength in Mpa 350 min. Elongation in % 15 min. Reduction of Area in % 40 min. Hardness in HB 121 max. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1020	SAE	USA	Sheet, Strip and Plate
1020	AISI	USA	Sheet, Strip and Plate
A 1040 1020	ASTM	USA	Steel
A 108 Grade 1020	ASTM	USA	Steel and Bar
A 29 1020	ASTM	USA	Steel and Bar
A 29 M1020	ASTM	USA	Steel and Bar
A 510 1020	ASTM	USA	Wire Rod and Round Wire

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)