

Material: SAE J403 | SAE J1397 UNS G10450 - Cold Drawn Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing

Group: Ferrous Mild Steel Alloys

Sub Group: SAE J403 | SAE J1397 UNS G10450 - Cold Drawn Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.430 - 0.500	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.600 - 0.900		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa 630 min. Yield Strength in Mpa 530 min. Elongation in % 12 min. Reduction of Area in % 35 min. Hardness in HB 179 max. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1045	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1045	AISI	USA	Steel and Bar
A 311 1045 Class A	ASTM	USA	Steel and Bar
A 311 1045 Class B	ASTM	USA	Steel and Bar
A 830 G10450	ASTM	USA	Plate and Steel
A 827 1045	ASTM	USA	Plate, Steel and Forging
A 682 Grade 1045	ASTM	USA	Steel and Strip

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com