

Material: SAE J403 | SAE J1397 UNS G11370 - Hot Rolled Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing

Group: Ferrous Mild Steel Alloys

Sub Group: SAE J403 | SAE J1397 UNS G11370 - Hot Rolled Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.320 - 0.390	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	1.350 - 1.650		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.080 - 0.130		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	610 min.
-	-	-	Yield Strength in Mpa	330 min.
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in BHN	179 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1137	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1137	AISI	USA	Steel and Bar
A 1040 1137	ASTM	USA	Steel
A 108 Grade 1137	ASTM	USA	Steel and Bar
A 29 1137	ASTM	USA	Steel and Bar
A 311 1137 Class A	ASTM	USA	Steel and Bar
A 510 1137	ASTM	USA	Wire Rod, Round Wire and Steel

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com