

Material: SAE J403 | SAE J1397 UNS G15270 - Cold Drawn Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing

Group: Ferrous Mild Steel Alloys

Sub Group: SAE J403 | SAE J1397 UNS G15270 - Cold Drawn Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.220 - 0.290	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	1.200 - 1.500		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	570 min.
-	-	-	Yield Strength in Mpa	480 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in BHN	163 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1527	SAE	USA	Plate, Strip, Sheets and Tubing
1527	AISI	USA	Steel
A 29 1527	ASTM	USA	Steel and Bar
A 510 1527	ASTM	USA	Wire Rod, Round Wire and Steel
A 576 15L27	ASTM	USA	Steel and Bar
A 830 1527	ASTM	USA	Plate and Steel
A 830 G15270	ASTM	USA	Plate and Steel

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com