

Material: SAE J403 UNS G10050

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets, Tubing

Group: Ferrous Stainless Steel Alloys

Sub Group: SAE J403 UNS G10050 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 max.	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.350 max.		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1005	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1005	AISI	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
A 29 1005	ASTM	USA	Bar
A 510 1005	ASTM	USA	Wire Rod
A 1040 1005	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1.03	ONORM	Australia	Wire Rod
1.0312	ONORM	Australia	Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com