

Material: SAE UNITEMP 750

Standard Specification for Nickel Alloy, Corrosion and Heat-Resistant, Wire

Group: Non-Ferrous Nickel Alloys

Sub Group: SAE UNITEMP 750 Nickel Alloy, Corrosion and Heat-Resistant, Wire

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.	As-Cast or Annealing or Age Hardening	
Silicon	Si %	0.500 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	15.500 max.		
Aluminium	Al %	0.700 max.		
Copper	Cu %	0.500 max.		
Ca + Ta	Ca% + Ta%	0.900 max.		
Titanium	Ti %	2.500 max.		
Iron	Fe %	8.000 max.		
Ni + Co	Ni% + Co%	73.000 min.		
-	-	-	Mechanical Properties Tensile Strength in Mpa 759 - 1897 Yield Strength in Mpa 345 - 1656 Elongation in % 2 - 45 Reduction of Area in % 30 - 60 Hardness in HRC 93 min. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Inconel X750	SAE	USA	Wire
N07750	UNS	USA	Wire
SIMALLOY	SAE	USA	Wire
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com