

Material: SFS 1.4308

Standard Specification for Steel Castings for General Engineering Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: SFS 1.4308 Steel Castings for General Engineering Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.070 max.	As Cast or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	1.500 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	18.000 - 20.000		
Nickel	Ni %	8.000 - 11.000		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	440 - 640
-	-	-	Yield Strength in Mpa	200 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	60 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
304C15	BS	British	Casting
304C15LT196	BS	British	Casting
2074/H5A	AS	Australia	Casting
2074/H5AM	AS	Australia	Casting
Z 6 CN 18-10 M	AFNOR NF	France	Casting
1.4308	NBN	Belgium	Casting
1.4308	DIN	Germany	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com