

Material: SFS 1.4848

Standard Specification for Steel Castings for General Engineering Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: SFS 1.4848 Steel Castings for General Engineering Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 - 0.500	As Cast or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	1.000 - 2.500		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	24.000 - 27.000		
Nickel	Ni %	19.000 - 22.000		
Niobium	Nb %	0.600 max.		
Tungsten	W %	0.600 max.		
Cobalt	Co %	1.000 max.		
			Mechanical Properties	
Vanadium	V %	0.120 max.	Tensile Strength in Mpa	450 min.
Copper	Cu %	0.250 max.	Yield Strength in Mpa	220 min.
Iron	Fe %	Balance	Elongation in %	8 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
310C45	BS	British	Casting
Z 40CN25.20-M	AFNOR NF	France	Casting
1.4848	CSN	Czech Republic	Casting
1.4848	DIN	Germany	Casting
1.4848	MSZ	Hungary	Casting
1.4848	AFNOR NF	France	Casting
1.4848	UNI	Italy	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com