

Material: SS 1.4309

Standard Specification for Steel Castings for General Engineering Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: SS 1.4309 Steel Castings for General Engineering Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	As Cast or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	1.500 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.025 max.		
Chromium	Cr %	18.000 - 20.000		
Nickel	Ni %	9.000 - 12.000		
Copper	Cu %	0.500 max.		
Nitrogen	N %	0.200 max.		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 440 - 640 Yield Strength in Mpa 210 min. Elongation in % 30 min. Reduction of Area in % - Hardness in BHN - Impact in Joule 80 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
304C12	BS	British	Casting
Z 2 CN 18-10 M	AFNOR NF	France	Casting
304 C 12 LT 196	BS	British	Casting
1.4309	ONORM	Australia	Casting
1.4309	UNE	Spain	Casting
1.4309	MSZ	Hungary	Casting
1.4309	UNI	Italy	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com