

Material: SS CW606N

Standard Specification for Copper and Copper Alloy Rod for Free Machining Purpose

Group: Non Ferrous Copper Alloys

Sub Group: SS CW606N Copper and Copper Alloy Rod for Free Machining Purpose

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Rod

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.050 max.	As Raw or Solution Heat Treated	
Iron	Fe %	0.200 max.		
Nickel	Ni %	0.300 max.		
Lead	Pb %	1.600 - 2.500		
Tin	Sn %	0.200 max.		
Other	Ot %	0.200 max.		
Copper	Cu %	61.000 - 62.000		
Zinc	Zn %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	290 - 686.5
-	-	-	Yield Strength in Mpa	147.1 - 451.1
-	-	-	Elongation in %	2 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HV	60 - 170
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 12164 CuZn37Pb2	DIN	Germany	Rod
CuZn37Pb2	BS	British	Rod
CW606N	BS	British	Rod
CuZn37Pb2	UNE	Spain	Rod
CW606N	UNE	Spain	Rod
CuZn37Pb2	CSN	Czech Republic	Rod
CuZn37Pb2	SS	Sweden	Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com