

Material: STAS T 6 CuMoNiCr 200

Standard Specification for Alloy Steel Casting

Group: Ferrous Stainless Steel Alloys

Sub Group: STAS T 6 CuMoNiCr 200 Alloy Steel Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 max.	Annealing or Hardening + Tempering	
Silicon	Si %	0.500 - 1.500		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	18.000 - 22.000		
Nickel	Ni %	24.000 - 26.000		
Molybdenum	Mo %	2.000 - 3.000		
Copper	Cu %	1.500 - 3.000		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 485 min. Yield Strength in Mpa 205 min. Elongation in % 35 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G X 2 NiCrMoCuN 25-20	DIN	Germany	Casting
J94650	UNS	USA	Casting
1.4536	DIN	Germany	Casting
A743 CN7MS	ASTM	USA	Casting
1.4536	DIN	Germany	Casting
A743 J94650	ASTM	USA	Casting
CN-7MS	NBR	Brazil	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com