

Material: UNE AM 8 Ni 18

Standard Specification for Ferritic Casting Steels for Low Temperatures

Group: Ferrous Mild Steel Alloys

Sub Group: UNE AM 8 Ni 18 Ferritic Casting Steels for Low Temperatures

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.	Normalizing or Annealing or Hardening + Tempering	
Silicon	Si %	0.300 - 0.600		
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.0350 max.		
Sulphur	S %	0.035 max.		
Nickel	Ni %	4.000 - 5.000		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 485 min. Yield Strength in Mpa 275 min. Elongation in % 24 min. Reduction of Area in % 35 min. Hardness in BHN - Impact in Joule 20 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
E2512	AISI	USA	Casting
GX 10 Ni 5	DIN	Germany	Casting
2512.0000	SAE	USA	Steel
Ao 10 Ni 20	MSZ	Hungary	Casting
J41501	UNS	USA	Casting
1.5681	DIN	Germany	Casting
A757 B4N B4Q	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com