

Material: UNE EN 1982 CuSn7Zn2Pb3-B

Standard Specification for Copper and Copper Alloys - Ingots and Castings

Group: Non-Ferrous Copper Alloy

Sub Group: UNE EN 1982 Copper and Copper Alloys - Ingots and Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.010 max.	As-Cast	
Iron	Fe %	0.200 max.		
Nickel	Ni %	2.000 max.		
Phosphorus	P %	0.030 max.		
Lead	Pb %	2.700 - 3.500		
Sulphur	S %	0.080 max.		
Antimony	Sb %	0.250 max.		
Silicon	Si %	0.010 max.		
Tin	Sn %	6.200 - 8.000		
Zinc	Zn %	1.700 - 3.200	Mechanical Properties Tensile Strength in Mpa 230 - 270 Yield Strength in Mpa 130 min. Elongation in % 12 - 14 Reduction of Area in % - Hardness in HB 65 - 70 Impact in Joule -	
Cu + Ni	Cu%+Ni%	85.000 - 88.500		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CB492K	BS	British	Tube
CB492K	UNE	Spain	Ingot and Casting
CB492K	ONORM	Australia	Ingot and Casting
CuSn7Zn2Pb3-B	ONORM	Australia	Ingot and Casting
CB492K	MSZ	Hungary	Ingot and Casting
CuSn7Zn2Pb3-B	MSZ	Hungary	Ingot and Casting
CB492K	AFNOR NF	France	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com