

# Material: UNE EN 1982 CuZn25Al5Mn4Fe3-C

## Standard Specification for Copper and Copper Alloys - Ingots and Castings

**Group:** Non-Ferrous Copper Alloy

**Sub Group:** UNE EN 1982 Copper and Copper Alloys - Ingots and Castings

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Ingot and Casting

| Chemical Composition |         |                 | Heat Treatment                                                                                                                                                                                             |  |
|----------------------|---------|-----------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--|
| Aluminium            | Al %    | 3.000 - 7.000   | As-Cast                                                                                                                                                                                                    |  |
| Iron                 | Fe %    | 1.500 - 4.000   |                                                                                                                                                                                                            |  |
| Manganese            | Mn %    | 2.500 - 5.000   |                                                                                                                                                                                                            |  |
| Nickel               | Ni %    | 3.000 max.      |                                                                                                                                                                                                            |  |
| Phosphorus           | P %     | 0.030 max.      |                                                                                                                                                                                                            |  |
| Lead                 | Pb %    | 0.200 max.      |                                                                                                                                                                                                            |  |
| Antimony             | Sb %    | 0.030 max.      |                                                                                                                                                                                                            |  |
| Silicon              | Si %    | 0.100 max.      |                                                                                                                                                                                                            |  |
| Tin                  | Sn %    | 0.200 max.      |                                                                                                                                                                                                            |  |
| Cu + Ni              | Cu%+Ni% | 60.000 - 67.000 |                                                                                                                                                                                                            |  |
| Zinc                 | Zn %    | Balance         | <b>Mechanical Properties</b><br>Tensile Strength in Mpa 680 - 750<br>Yield Strength in Mpa 450 - 580<br>Elongation in % 1 - 8<br>Reduction of Area in % -<br>Hardness in HB 180 - 190<br>Impact in Joule - |  |
| -                    | -       | -               |                                                                                                                                                                                                            |  |
| -                    | -       | -               |                                                                                                                                                                                                            |  |
| -                    | -       | -               |                                                                                                                                                                                                            |  |
| -                    | -       | -               |                                                                                                                                                                                                            |  |
| -                    | -       | -               |                                                                                                                                                                                                            |  |

| Cross Reference Table |          |           |                              |
|-----------------------|----------|-----------|------------------------------|
| Material              | Standard | Country   | Grade Belong to the Industry |
| CB762S                | BS       | British   | Ingot and Casting            |
| CC762S                | ONORM    | Australia | Ingot and Casting            |
| CC762S                | BDS      | Bulgaria  | Ingot and Casting            |
| CC762S                | UNI      | Italy     | Ingot and Casting            |
| CC762S                | DIN      | Germany   | Ingot and Casting            |
| CuZn25Al5Mn4Fe3-C     | MSZ      | Hungary   | Ingot and Casting            |
| CuZn25Al5Mn4Fe3-C     | AFNOR NF | France    | Ingot and Casting            |

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

**Customer Care:** +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)