

Material: UNE EN 1982 CuZn39Pb1AlB-C

Standard Specification for Copper and Copper Alloys - Ingots and Castings

Group: Non-Ferrous Copper Alloy

Sub Group: UNE EN 1982 Copper and Copper Alloys - Ingots and Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.400 - 0.700	As-Cast	
Iron	Fe %	0.050 - 0.200		
Manganese	Mn %	0.050 max.		
Nickel	Ni %	0.200 max.		
Lead	Pb %	1.200 - 1.700		
Silicon	Si %	0.050 max.		
Tin	Sn %	0.300 max.		
Copper	Cu %	59.500 - 61.000		
Zinc	Zn %	Balance	Mechanical Properties Tensile Strength in Mpa 310 - 350 Yield Strength in Mpa 180 - 210 Elongation in % 3 - 13 Reduction of Area in % - Hardness in HB 90 - 100 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CB755S	BS	British	Ingot and Casting
CC755S	DIN	Germany	Ingot and Casting
CC755S	MSZ	Hungary	Ingot and Casting
CC755S	UNI	Italy	Ingot and Casting
CC755S	AFNOR NF	France	Ingot and Casting
CuZn39Pb1AlB-C	CSN	Czech Republic	Ingot and Casting
CuZn39Pb1AlB-C	MSZ	Hungary	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com