

# Material: UNE EN-JS1050

## Standard Specification For Spheoidal Graphite Cast Irons Castings

**Group:** Ferrous SG Iron / Ductile Iron Alloys

**Sub Group:** UNE EN-JS1050 Spheoidal Graphite Cast Irons Castings

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Casting

Chemical Composition		
Carbon	C %	-
Silicon	Si %	-
Manganese	Mn %	-
Phosphorus	P %	-
Sulphur	S %	-
Chromium	Cr %	-
Nickel	Ni %	-
Copper	Cu %	-
Iron	Fe %	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast

Mechanical Properties	
Tensile Strength in Mpa	500 min.
Yield Strength in Mpa	290 min.
Elongation in %	7 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
JS 500-7	ISO	International	Casting
JS 500-7	AS	Australia	Casting
EN-GJS-500-7	BS	British	Casting
5.3200	SS	Sweden	Casting
FCD 500-7	JIS	Japan	Casting
EN-JS1040	DIN	Germany	Casting
5.3200	EN	European Union	Casting

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India