

Material: UNE F.1430

Standard Specification for Mild Steel Alloys Bar and Rod

Group: Ferrous Mild Steel Alloys

Sub Group: UNE F.1430 Mild Steel Alloys Bar and Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bar and Rod

Chemical Composition		
Carbon	C %	0.470 - 0.550
Silicon	Si %	0.400 max.
Manganese	Mn %	0.700 - 1.100
Phosphorus	P %	0.035 max.
Sulphur	S %	0.035 max.
Chromium	Cr %	0.900 - 1.200
Vanadium	V %	0.100 - 0.250
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As Raw or Annealing or Normalizing or Hardening and Tempering

Mechanical Properties	
Tensile Strength in Mpa	800 - 950
Yield Strength in Mpa	600 min.
Elongation in %	13 min.
Reduction of Area in %	-
Hardness in BHN	As Per HT
Impact in Joule	30 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
51CrV4	EN	European Union	Bar and Rod
1.8159	EN	European Union	Bar and Rod
35 NCD 16	AFNOR NF	France	Bar and Rod
50 CV 4	AFNOR NF	France	Bar and Rod
50 CV 4	DIN	Germany	Bar and Rod
15 260	CSN	Czech Republic	Bar and Rod
CrV 3	MSZ	Hungary	Bar and Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India