

Material: UNE X 2 CrMoTiNb 18-2

Standard Specification for Stainless Steels Plate, Sheet and Strip

Group: Ferrous Stainless Steel Alloys

Sub Group: UNE 36016-2 Stainless Steels Plate, Sheet and Strip

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.025 max.	Normalizing or Annealing or Hardening + Tempering	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	17.500 - 19.500		
Molybdenum	Mo %	1.750 - 2.500		
Nickel	Ni %	1.000 max.		
Nitrogen	N %	0.035 max.		
Ti+Nb	Ti% + Nb%	0.800 max.		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 415 min. Yield Strength in Mpa 275 min. Elongation in % 20 min. Reduction of Area in % - Hardness in HB 217 max. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
444.0000	AS	Australia	Plate, Sheet and Strip
A176 S44400	ASTM	USA	Plate, Sheet and Strip
F.3123	UNE	Spain	Casting
S44400	UNS	USA	Plate, Sheet and Strip
SA-731 18 Cr-2Mo	ASTM	USA	Casting
444	SAE	USA	Plate, Sheet and Strip
A731 18Cr-2Mo	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com