

Material: UNE ZnAl4Cu1

Standard Specification For Zinc Alloy Ingots

Group: Non-Ferrous Zinc Alloys

Sub Group: UNE ZnAl4Cu1 Zinc Alloy Ingots

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Ingot

Chemical Composition			Heat Treatment	
Aluminium	Al %	3.800 - 4.200	As-Cast	
Copper	Cu %	0.700 - 1.100		
Magnesium	Mg %	0.035 - 0.060		
Lead	Pb %	0.003 max.		
Cadmium	Cd %	0.003 max.		
Tin	Sn %	0.001 max.		
Iron	Fe %	0.020 max.		
Nickel	Ni %	0.001 max.		
Silicon	Si %	0.020 max.		
Zinc	Zn %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 330 min. Yield Strength in Mpa 250 min. Elongation in % 5 min. Reduction of Area in % - Hardness in HB 92 min. Impact in Joule 58 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
ZP5	DIN	Germany	Casting
Alloy B	BS	British	Casting
G-ZnAl4Cu1	UNI	Italy	Ingot
ZnAl4Cu1	NS	Norway	Ingot
ZnAl4Cu1	SS	Sweden	Ingot
B 240 AC41A	ASTM	USA	Ingot and Casting
2.2141	DIN	Germany	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com