

Material: UNE ZnAl4Cu3

Standard Specification For Zinc Alloy Ingots

Group: Non-Ferrous Zinc Alloys

Sub Group: UNE ZnAl4Cu3 Zinc Alloy Ingots

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Ingot

Chemical Composition			Heat Treatment	
Aluminium	Al %	3.800 - 4.200	As-Cast	
Copper	Cu %	2.700 - 3.300		
Magnesium	Mg %	0.035 - 0.060		
Cadmium	Cd %	0.003 max.		
Tin	Sn %	0.001 max.		
Iron	Fe %	0.020 max.		
Lead	Pb %	0.003 max.		
Silicon	Si %	0.020 max.		
Nickel	Ni %	0.001 max.		
Zinc	Zn %	Balance	Mechanical Properties Tensile Strength in Mpa 335 min. Yield Strength in Mpa 270 min. Elongation in % 5 min. Reduction of Area in % - Hardness in HB 102 min. Impact in Joule 59 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
ZP2	DIN	Germany	Casting
G-ZnAl4Cu3	UNI	Italy	Ingot
B 240 AC43A	ASTM	USA	Ingot and Casting
GB-ZnAl4Cu3	DIN	Germany	Ingot and Casting
GK-ZnAl4Cu3	DIN	Germany	Casting
2.2143	DIN	Germany	Casting
2.2143.01	DIN	Germany	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com