

Material: UNI 1.0213

Standard Specification for Steel Castings for Pressure Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: UNI 1.0213 Castings for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 - 0.100	Normalizing or Quenching or Solution Annealing	
Silicon	Si %	0.100 max.		
Manganese	Mn %	0.200 - 0.450		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.025 max.		
Aluminium	Al %	0.020 - 0.060		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 490 min. Yield Strength in Mpa - Elongation in % - Reduction of Area in % 63 max. Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 10213 G17CrMo5-5	BS	British	Plate, Tubes and Forging
QSt 34-3	DIN	Germany	Plate, Tubes and Forging
C8C	ISO	International	Casting
1.0213	EN	European Union	Casting
1.0213	AFNOR NF	France	Casting
1.0213	DIN	Germany	Casting
1.0213	MSZ	Hungary	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com