

Material: UNI EN 12420 CuZn39Pb2

Standard Specification for Copper and Copper-Alloy Forgings

Group: Non-Ferrous Copper Alloy

Sub Group: UNI EN 12420 Copper and Copper-Alloy Forgings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Forging

Chemical Composition		
Aluminium	Al %	0.050 max.
Iron	Fe %	0.300 max.
Nickel	Ni %	0.300 max.
Other	Ot%	0.200 max.
Lead	Pb %	1.600 - 2.500
Tin	Sn %	0.300 max.
Copper	Cu %	59.000 - 60.000
Zinc	Zn %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Normalizing or Annealing or Tempering

Mechanical Properties	
Tensile Strength in Mpa	350 - 570
Yield Strength in Mpa	140 - 510
Elongation in %	5 - 30
Reduction of Area in %	-
Hardness in HB	70 - 145
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B981 C37700	ASTM	USA	Rod, Bar, Wire and Shapes
CW612N	UNI	Italy	Forging
CW612N	ONORM	Australia	Forging
B283 C37700	ASTM	USA	Forging
SB-283 C37700	ASME	USA	Forging
CA377	SAE	USA	Forging
C37700	UNS	USA	Rod, Bar, Tube and Shapes

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 **Email:** info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India