

Material: UNI G 17 Mn 5

Standard Specification for Steel Castings for Pressure Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: UNI G 17 Mn 5 Steel Castings for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 - 0.200	Normalizing or Quenching or Solution Annealing	
Silicon	Si %	0.600 max.		
Manganese	Mn %	1.000 - 1.600		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	0.300 max.		
Molybdenum	Mo %	0.120 max.		
Nickel	Ni %	0.400 max.		
Copper	Cu %	0.300 max.		
Vanadium	V %	0.030 max.		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 450 - 600 Yield Strength in Mpa 240 min. Elongation in % 24 min. Reduction of Area in % - Hardness in BHN - Impact in Joule 70 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 10213 G17Mn5	BS	British	Plate, Tubes and Forging
GS-16 Mn 5	DIN	Germany	Plate, Tubes and Forging
SC 480	JIS	Japan	Casting
SCW 480	JIS	Japan	Casting
SCW 490-CF	JIS	Japan	Casting
G 17 Mn 5	MSZ	Hungary	Casting
G 17 Mn 5	UNE	Spain	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com