

## Material: UNI G X 35 Cr 28

### Standard Specification for Martensitic Stainless Steel; Heat Resisting Steel and Alloy Sand Castings

**Group:** Ferrous Stainless Steel Alloys

**Sub Group:** UNI G X 35 Cr 28 Martensitic Stainless Steel; Heat Resisting Steel and Alloy Sand Castings

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 - 0.500	As - Cast	
Silicon	Si %	2.500 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	26.000 - 30.000		
Nickel	Ni %	4.000 max.		
Molybdenum	Mo %	0.500 max.		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	380 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
452 C 11	BS	British	Casting
1.4823	DIN	Germany	Casting
J92605	UNS	USA	Casting
40 CrNiSi 25-4	MSZ	Hungary	Casting
G X 40 CrNiSi 27-4	DIN	Germany	Casting
A297 Grade HD	ASTM	USA	Casting
A297 Grade HC	ASTM	USA	Casting

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)