

Material: UNI G X 40 CrNi 26-20

Standard Specification for Austenitic Stainless Steel, Heat Resisting Steel and Alloy Sand

Group: Ferrous Stainless Steel Alloys

Sub Group: UNI G X 40 CrNi 26-20 Austenitic Stainless Steel, Heat Resisting Steel and Alloy Sand Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 - 0.600	Solution Annealing	
Silicon	Si %	2.500 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	24.000 - 28.000		
Nickel	Ni %	18.000 - 22.000		
Molybdenum	Mo %	0.500 max.		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	440 min.
-	-	-	Yield Strength in Mpa	240 min.
-	-	-	Elongation in %	10 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A351 HK30	ASTM	USA	Casting
SA 351 HK30	ASME	USA	Casting
310 C40	BS	British	Casting
F.8452	UNE	Spain	Casting
A608 HK30	ASTM	USA	Casting
422952	CSN	Czech Republic	Casting
393 G-X 40 CrNi 25 20	SFS	Finland	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com