

## Material: UNS C63200

### Standard Specification for Copper and Copper Alloy Forging Rod, Bar and Shapes

**Group:** Non-Ferrous Copper Alloy

**Sub Group:** ASTM B124 Copper and Copper Alloy Forging Rod, Bar and Shapes

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Rod, Bar and Shape

Chemical Composition			Heat Treatment	
Lead	Pb %	0.050 max.	Normalizing or Annealing or Tempering	
Tin	Sn %	0.200 max.		
Iron	Fe %	0.300 max.		
Ni + Cu	Ni% + Cu%	0.250 max.		
Silicon	Si %	1.500 - 2.200		
Manganese	Mn %	0.100 max.		
Arsenic	As %	0.150 max.		
Aluminium	Al %	6.300 -7.600		
Zinc	Zn %	0.500 max.		
Copper	Cu %	Balance		
-	-	-	<b>Mechanical Properties</b> Tensile Strength in Mpa      344 min. Yield Strength in Mpa      - Elongation in %      - Reduction of Area in %      - Hardness in BHN      - Impact in Joule      -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B124 C63200	ASTM	USA	Rod, Bar and Shapes
B150 C63200	ASTM	USA	Rod, Bar and Shapes
B171 C63200	ASTM	USA	Rod, Bar and Shapes
B283 C63200	ASTM	USA	Forging
SB-150 C63200	ASME	USA	Rod, Bar and Shape
SB-171 C63200	ASME	USA	Plate and Sheet
SB-283 C63200	ASME	USA	Forging

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)