

Material: UNS J02503

Standard Specification for Carbon Steel Casting

Group: Ferrous Mild Steel Alloys

Sub Group: UNS J02503 Carbon Steel Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.250 max.	Normalizing or Annealing or Hardening + Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	1.200 max.		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	0.500		
Nickel	Ni %	0.500 max.		
Molybdenum	Mo %	0.200 max.		
Vanadium	V %	0.030 max.		
Copper	Cu %	0.300 max.		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 485- 655 Yield Strength in Mpa 275 min. Elongation in % 22 min. Reduction of Area in % 35 min. Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A660 WCA	ASTM	USA	Fusion Welding, Bending and Forming
SA 660 WCC	ASME	USA	Centrifugal Casting
SA 216 WCC	ASME	USA	Casting
1.0619	EN	European Union	Casting
1.0619	DIN	Germany	Casting
A216 WCB	ASTM	USA	Casting
A216 WCC	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com