

Material: UNS J03501

Standard Specification for Carbon Steel Casting

Group: Ferrous Mild Steel Alloys

Sub Group: UNS J03501 Carbon Steel Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.350 max.	Normalizing or Annealing or Hardening + Tempering	
Silicon	Si %	0.800 max.		
Manganese	Mn %	0.700 max.		
Phosphorus	P %	0.050 max.		
Sulphur	S %	0.060 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa 485 min. Yield Strength in Mpa 250 min. Elongation in % 22 min. Reduction of Area in % 30 min. Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A27 Grade N-1	ASTM	USA	Casting
A27 Grade U-60-30	ASTM	USA	Casting
A27 Grade 60-30	ASTM	USA	Casting
A27 Grade 65-35	ASTM	USA	Casting
A27 Grade 70-36	ASTM	USA	Casting
A27 Grade 70-40	ASTM	USA	Casting
A27 Grade N-2	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India