

Material: UNS J13047

Standard Specification for Alloy Steel Casting

Group: Ferrous Mild Steel Alloys

Sub Group: UNS J13047 Alloy Steel Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 max.	Annealing or Normalizing or Hardening + Tempering	
Silicon	Si %	0.800 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	0.400 - 0.800		
Nickel	Ni %	0.400 - 0.800		
Molybdenum	Mo %	0.150 - 0.300		
Copper	Cu %	0.500 max.	Mechanical Properties	
Vanadium	V %	0.030 max.	Tensile Strength in Mpa	724 min.
Tungsten	W %	0.100 max.	Yield Strength in Mpa	586 min.
Iron	Fe %	Balance	Elongation in %	10 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
8620.0000	AISI	USA	Forging, Bar, Wire, and Shape
8620	SAE	USA	Bar, Wire, Sheet, Strip and Forging
A487 4A	ASTM	USA	Casting
J12048	UNS	USA	Casting
A487 4B	ASTM	USA	Casting
A487 4C	ASTM	USA	Casting
A487 4D	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com