

Material: UNS J14045

Standard Specification for Alloy Steel Casting

Group: Ferrous Mild Steel Alloys

Sub Group: UNS J14045 Alloy Steel Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.380 - 0.400	As- Cast or Normalizing or Annealing or Hardening + Tempering	
Manganese	Mn %	0.700 - 1.100		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	0.800 - 1.100		
Molybdenum	Mo %	0.150 - 0.250		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa - Yield Strength in Mpa - Elongation in % - Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A915 Grade SC 4140	ASTM	USA	Casting
4140	AISI	USA	Bar, Wire, Tube and Forging
4140	SAE	USA	Bar, Wire, Tube and Forging
4140	AS	Australia	Bar, Wire, Tube and Forging
4140	AMS	USA	Bar, Wire, Tube and Forging
A 29 4140	ASTM	USA	Bar, Wire, Tube and Forging
A 505 4140	ASTM	USA	Bar, Wire, Tube and Forging

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com