

Material: UNS J42045

Standard Specification for Alloy Steel Casting

Group: Ferrous Mild Steel Alloys

Sub Group: UNS J42045 Alloy Steel Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 max.	Normalizing or Annealing or Hardening + Tempering	
Silicon	Si %	0.750 max.		
Manganese	Mn %	0.400 - 0.700		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.045 max.		
Chromium	Cr %	4.000 - 6.500		
Molybdenum	Mo %	0.450 - 0.650		
Nickel	Ni %	0.500 max.		
Tungsten	W %	0.100 max.		
Copper	Cu %	0.500 max.		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 620 - 795 Yield Strength in Mpa 415 min. Elongation in % 18 min. Reduction of Area in % 35 min. Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A426 Grade CP5	ASTM	USA	Casting
G S 12 CrMo 19-5	DIN	Germany	Casting
G X 15 CrMo 5	EN	European Union	Casting
SCPH 61	JIS	Japan	Casting
1.7363	DIN	Germany	Casting
G X 12 CrMo 5	DIN	Germany	Casting
A217 Grade C5	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com