

Material: UNS J92130

Standard Specification for Alloy Steel Casting

Group: Ferrous Stainless Steel Alloys

Sub Group: UNS J92130 Alloy Steel Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.070 max.	Normalizing or Annealing or Hardening + Tempering	
Silicon	Si %	1.000 max.		
Manganese	Mn %	0.700 max.		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	14.000 - 15.500		
Nickel	Ni %	4.200 - 5.500		
Copper	Cu %	2.500 - 3.200		
Nitrogen	N %	0.050 max.		
Niobium	Nb %	0.150 - 0.350		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	1170 min.
-	-	-	Yield Strength in Mpa	1000 min.
-	-	-	Elongation in %	5 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	375 min.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J92110	UNS	USA	Casting
SA-747 CB7Cu-2	ASME	USA	Casting
5356	AMS	USA	Casting
AMS 5346	SAE	USA	Casting
5400	AMS	USA	Casting
5357	AMS	USA	Casting
A747 CB7CU-2	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com