

Material: UNS J93413

Standard Specification for Alloy Steel Casting

Group: Ferrous Stainless Steel Alloys

Sub Group: UNS J93413 Alloy steel casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 - 0.400	As - Cast	
Silicon	Si %	0.500 - 2.000		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	26.000 - 30.000		
Nickel	Ni %	8.000 - 11.000		
Molybdenum	Mo %	0.500 max.		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 550 min. Yield Strength in Mpa 275 min. Elongation in % 10 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SCH 18	JIS	Japan	Casting
J94013	UNS	USA	Casting
A608 Grade HI 35	ASTM	USA	Casting
SCH 17	JIS	Japan	Casting
J93403	UNS	USA	Casting
A 608 G HE35	ASTM	USA	Casting
A297 Grade HE	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com