

Material: UNS N06920

Standard Specification for Nickel-Chromium-Iron-Molybdenum-Tungsten Alloy Plate, Sheet and Strip

Group: Non-Ferrous Nickel Alloys

Sub Group: UNS N06920 Nickel-Chromium-Iron-Molybdenum-Tungsten Alloy Plate, Sheet and Strip

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	20.500 - 23.000		
Sulphur	S %	0.030 max.		
Molybdenum	Mo %	8.000 - 10.000		
Phosphorus	P %	0.040 max.		
Cobalt	Co %	5.000 max.		
Iron	Fe %	17.000 - 20.000		
Tungsten	W %	1.000 - 3.000		
Nickel	Ni %	Balance	Mechanical Properties Tensile Strength in Mpa 655 min. Yield Strength in Mpa 240 min. Elongation in % 35 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 814 N06920	ASTM	USA	Plate, Sheet and Strip
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com