

Material: UNS N08604

Standard Specification for Castings, Iron-Chromium Alloy Casting

Group: Ferrous Stainless Steel Alloys

Sub Group: UNS N08604 Castings, Iron-Chromium Alloy Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 - 0.600	As - Cast	
Silicon	Si %	2.000 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	28.000 - 32.000		
Molybdenum	Mo %	0.500 max.		
Nickel	Ni %	16.000 - 22.000		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	450 min.
-	-	-	Yield Strength in Mpa	240 min.
-	-	-	Elongation in %	10 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SCH 23	JIS	Japan	Casting
A608 Grade HL 30	ASTM	USA	Casting
A608 Grade HL 40	ASTM	USA	Casting
N08613	UNS	USA	Casting
N08614	UNS	USA	Casting
A297 Grade HL	ASTM	USA	Casting
IS 4522 Grade 10	IS	India	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com