

Material: UNS N26625

Standard Specification for Castings, Nickel and Nickel Alloy

Group: Non-Ferrous Nickel Alloys

Sub Group: UNS N26625 Castings, Nickel and Nickel Alloy

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.060 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	1.000 max.
Phosphorus	P %	0.015 max.
Sulphur	S %	0.015 max.
Chromium	Cr %	20.000 - 23.000
Niobium	Nb %	3.150 - 4.500
Molybdenum	Mo %	8.000 - 10.000
Iron	Fe %	5.000 max.
Nickel	Ni %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast or Annealing or Age Hardning

Mechanical Properties	
Tensile Strength in Mpa	485 min.
Yield Strength in Mpa	275 min.
Elongation in %	25 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A 494 CW6MC	ASTM	USA	Casting
SA-494 CW6MC	ASME	USA	Casting
C-NiCr22Mo9Nb4	AFNOR NF	France	Casting
NC22D9Nb4-M	AFNOR NF	France	Casting
NC6625	AFNOR NF	France	Casting
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India