

Material: UNS R30008

Standard Specification for Castings, Cobalt-Based alloy

Group: Non-Ferrous Cobalt Alloys

Sub Group: UNS R30008 Castings, Cobalt-Based alloy

Application: Intended for Valve, Pump, General Engineering, Automotive, Medical and other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.	As-Cast or Annealing	
Chromium	Cr %	18.500 - 21.500		
Molybdenum	Mo %	6.500 - 7.500		
Nickel	Ni %	15.000 - 18.000		
Cobalt	Co %	39.000 - 42.000		
Silicon	Si %	1.200 max.		
Manganese	Mn %	1.000 - 2.000		
Sulphur	S %	0.015 max.		
Phosphorus	P %	0.015 max.		
Beryllium	Be %	0.001 max.		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 850 min. Yield Strength in Mpa 450 min. Elongation in % 1 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
F1058 Grade 1	ASTM	USA	Wire and Strip
F 2527 R30003	ASTM	USA	Casting
7402-4	JIS	Japan	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com