

Material: UNS R30075

Standard Specification for Cobalt-Based alloy

Group: Non-Ferrous Cobalt Alloys

Sub Group: UNS R30075 Cobalt-Based alloy

Application: Intended for Valve, Pump, General Engineering, Automotive, Medical and other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.350 max.	As-Cast or Annealing	
Chromium	Cr %	27.000 - 30.000		
Molybdenum	Mo %	5.000 - 7.000		
Nickel	Ni %	1.000 max.		
Iron	Fe %	0.750 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Tungsten	W %	0.200 max.		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.010 max.		
Nitrogen	N %	0.250 max.	Mechanical Properties	
Aluminium	Al %	0.300 max.	Tensile Strength in Mpa	655 min.
Boron	B %	0.010 max.	Yield Strength in Mpa	450 min.
Cobalt	Co %	Balance	Elongation in %	8 min.
-	-	-	Reduction of Area in %	-
			Hardness in HRC	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
F 75 R30075	ASTM	USA	Casting
7402-1	JIS	Japan	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com