

Material: UNS R30563

Standard Specification for Cobalt-Based alloy

Group: Non-Ferrous Cobalt Alloys

Sub Group: UNS R30563 Cobalt-Based alloy

Application: Intended for Valve, Pump, General Engineering, Automotive, Medical and other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 max.	As-Cast or Annealing	
Chromium	Cr %	18.000 - 22.000		
Molybdenum	Mo %	3.000 - 4.000		
Nickel	Ni %	15.000 - 25.000		
Iron	Fe %	4.000 - 6.000		
Silicon	Si %	0.500 max.		
Manganese	Mn %	1.000 max.		
Sulphur	S %	0.010 max.		
Tungsten	W %	3.000 - 4.000		
Titanium	Ti %	0.500 - 3.500		
Cobalt	Co %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	600 min.
-	-	-	Yield Strength in Mpa	275 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
F 563 R30563	ASTM	USA	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com