

Material: UNS Z35636

Standard Specification for Zinc-Aluminum ZA-8 Alloy Casting

Group: Non-Ferrous Zinc Alloy

Sub Group: UNS Zinc-Aluminum ZA-8 Alloy Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition		
Aluminium	Al %	8.000 - 8.800
Cadmium	Cd %	0.006 max.
Copper	Cu %	0.800 - 1.300
Iron	Fe %	0.075 max.
Magnesium	Mg %	0.015 - 0.030
Lead	Pb %	0.006 max.
Tin	Sn %	0.003 max.
Zinc	Zn %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast or Aging

Mechanical Properties	
Tensile Strength in Mpa	221 - 374
Yield Strength in Mpa	198 - 290
Elongation in %	1 - 10
Reduction of Area in %	-
Hardness in HB	85 - 103
Impact in Joule	20 - 42 @RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
ZA-8	ANSI/AA	USA	Casting
B86 ZA-8	ASTM	USA	Casting
ZP8	ISO	International	Casting
ZP0810	ISO	International	Casting
Z35638	UNS	USA	Casting
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India