

Material: ANSI/AA A360

Standard Specification for Aluminium Alloy for General Engineering and Light-Weight Structural Purpose

Group: Non-Ferrous Aluminium Alloy

Sub Group: ANSI/AA Aluminium Alloy for General Engineering and Light-Weight Structural Purpose

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Silicon	Si %	9.000 - 10.000	As-Cast	
Iron	Fe %	1.300 max.		
Copper	Cu %	0.600 max.		
Magnesium	Mg %	0.400 - 0.600		
Manganese	Mn %	0.350 max.		
Nickel	Ni %	0.500 max.		
Zinc	Zn %	0.500 max.		
Tin	Sn %	0.150 max.		
Other	Ot%	0.250 max.		
Aluminium	Al %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 317 min. Yield Strength in Mpa 165 min. Elongation in % 3.5 min. Reduction of Area in % - Hardness in BHN 75 min. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A03600	UNS	USA	Casting
B 275 360.0	ASTM	USA	Casting
A 275 SG100B	ASTM	USA	Casting
B 85 360.0	ASTM	USA	Casting
B 85 SG100B	ASTM	USA	Casting
A03600	SAE	USA	Casting
360.0	NBR	Brazil	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com