

Material: ANSI/AA Zamak 3

Specification Standards for Die Castings

Group: Non-Ferrous Zinc Alloy

Sub Group: ANSI/AA for Die Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	3.700 - 4.300	As-Cast or Aging	
Magnesium	Mg %	0.020 - 0.060		
Copper	Cu %	0.100 max.		
Iron	Fe %	0.050 max.		
Lead	Pb %	0.005 max.		
Cadmium	Cd %	0.004 max.		
Tin	Sn %	0.002 max.		
Zinc	Zn %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 283 min. Yield Strength in Mpa 221 min Elongation in % 10 min. Reduction of Area in % - Hardness in HB 82 min. Impact in Joule 58 min.	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
ZP3	ISO	International	Casting
Z33521	UNS	USA	Ingot and Casting
B86 Alloy 3	ASTM	USA	Casting
B86 Zamak 3	ASTM	USA	Casting
B86 AG40A	ASTM	USA	Casting
ZnAl4	UNI	Italy	Ingot and Casting
B240 Zamak 3	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com