

Material: ASTM F 2527 R30035

Standard Specification for Seamless Cobalt Alloy Small Diameter Tubing for Surgical Implants

Group: Non-Ferrous Cobalt Alloys

Sub Group: ASTM F 2527 R30035 Seamless Cobalt Alloy Small Diameter Tubing for Surgical Implants

Application: Intended for Valve, Pump, General Engineering, Automotive, Medical and other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.025 max.	As-Cast or Annealing	
Chromium	Cr %	19.000 - 21.000		
Molybdenum	Mo %	9.000 - 10.500		
Nickel	Ni %	33.000 - 37.000		
Iron	Fe %	1.000 max.		
Silicon	Si %	0.150 max.		
Manganese	Mn %	0.150 max.		
Phosphorus	P %	0.015 max.		
Sulphur	S %	0.010 max.		
Titanium	Ti %	1.000 max.		
			Mechanical Properties	
Boron	B %	0.015 max.	Tensile Strength in Mpa	793 - 2482
Cobalt	Co %	Balance	Yield Strength in Mpa	241 - 586
-	-	-	Elongation in %	1.800 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in HRC	43 min.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
F562 R30035	ASTM	USA	Casting
R30035	UNS	USA	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com