

## Material: ASTM F467 C67500

### Standard Specification for Nonferrous Nuts for General Use

**Group:** Non-Ferrous Copper Alloy

**Sub Group:** ASTM F467 Nonferrous Nuts for General Use

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Nut

| Chemical Composition |      |                 | Heat Treatment                                                                                                                                                                                    |  |
|----------------------|------|-----------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--|
| Aluminium            | Al % | 0.250 max.      | Normalizing or Annealing or Tempering                                                                                                                                                             |  |
| Iron                 | Fe % | 0.800 - 2.000   |                                                                                                                                                                                                   |  |
| Manganese            | Mn % | 0.050 - 0.500   |                                                                                                                                                                                                   |  |
| Lead                 | Pb % | 0.200 max.      |                                                                                                                                                                                                   |  |
| Tin                  | Sn % | 0.500 - 1.500   |                                                                                                                                                                                                   |  |
| Copper               | Cu % | 57.000 - 60.000 |                                                                                                                                                                                                   |  |
| Zinc                 | Zn % | Balance         |                                                                                                                                                                                                   |  |
| -                    | -    | -               | <b>Mechanical Properties</b><br>Tensile Strength in Mpa -<br>Yield Strength in Mpa 379.2 - 406.8<br>Elongation in % -<br>Reduction of Area in % -<br>Hardness in HRB 60 min.<br>Impact in Joule - |  |
| -                    | -    | -               |                                                                                                                                                                                                   |  |
| -                    | -    | -               |                                                                                                                                                                                                   |  |
| -                    | -    | -               |                                                                                                                                                                                                   |  |
| -                    | -    | -               |                                                                                                                                                                                                   |  |
| -                    | -    | -               |                                                                                                                                                                                                   |  |
| -                    | -    | -               |                                                                                                                                                                                                   |  |
| -                    | -    | -               |                                                                                                                                                                                                   |  |
| -                    | -    | -               |                                                                                                                                                                                                   |  |

| Cross Reference Table |          |         |                                 |
|-----------------------|----------|---------|---------------------------------|
| Material              | Standard | Country | Grade Belong to the Industry    |
| B124 C67500           | ASTM     | USA     | Rod, Bar and Shapes             |
| B138 C67500           | ASTM     | USA     | Rod, Bar and Shape              |
| B283 C67500           | ASTM     | USA     | Forging                         |
| CA675                 | SAE      | USA     | Rod, Bar and Shape              |
| SB-283 C67500         | ASME     | USA     | Forging                         |
| SF-467 C67500         | ASME     | USA     | Nut                             |
| SF-468 C67500         | ASME     | USA     | Bolts, Hex Cap Screws and Studs |

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India