

Material: KS D 3592 SWRCH8A

Standard Specification for Carbon Steel Wire Rods for Cold Heading and Cold Forging

Group: Ferrous Mild Steel Alloys

Sub Group: KS D 3592 SWRCH8A Carbon Steel Wire Rods for Cold Heading and Cold Forging

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Wire Rod and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 max.	As Raw or Normalizing or Annealing or Hardening and Tempering	
Silicon	Si %	0.100 max.		
Manganese	Mn %	0.600 max.		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.035 max.		
Aluminium	Al %	0.020 min.		
Chromium	Cr %	0.200 max.		
Copper	Cu %	0.300 max.		
Nickel	Ni %	0.200 max.		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 490 max. Yield Strength in Mpa - Elongation in % - Reduction of Area in % 63 min. Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SWRCH 8A	JIS	Japan	Wire Rod and Forging
SWCH 8A	JIS	Japan	Wire Rod and Forging
SWRCH8A	MS	Malaysia	Wire Rod and Forging
C8C	ISO	International	Wire Rod and Forging
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com