

Material: KS NW6601

Standard Specification for Nickel and Nickel Alloy Wire and Drawing Stock

Group: Non-Ferrous Nickel Alloys

Sub Group: KS NW6601 Nickel and Nickel Alloy Wire and Drawing Stock

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	21.000 - 25.000		
Aluminium	Al %	1.000 - 1.700		
Copper	Cu %	1.000 max.		
Sulphur	S %	0.015 max.		
Nickel	Ni %	58.000 - 63.000		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	515 min.
-	-	-	Yield Strength in Mpa	170 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Inconel 601	SAE	USA	Plate, Sheet and Strip
N06601	UNS	USA	Plate, Sheet and Strip
NiCr23Fe15Al	JIS	Japan	Plate, Sheet and Strip
NW6601	JIS	Japan	Plate, Sheet and Strip
NiCr23Fe15Al	KS	Korea	Wire
B516 N06601	ASTM	USA	Tube
F2281 601	ASTM	USA	Bolts, Hex Cap Screws and Studs

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com