

Material: KS STS 350

Standard Specification for Austenitic Chromium Nickel Molybdenum Nitrogen Stainless Steel

Group: Ferrous Stainless Steel Alloys

Sub Group: KS STS 350 Austenitic Chromium Nickel Molybdenum Nitrogen Stainless Steel

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	22.000 - 24.000		
Nickel	Ni %	20.000 - 23.000		
Molybdenum	Mo %	6.000 - 6.8000		
Copper	Cu %	0.400 max.		
Nitrogen	N %	0.210 - 0.320		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Tensile Strength in Mpa	674 min.
			Yield Strength in Mpa	330 min.
			Elongation in %	40 min.
			Reduction of Area in %	-
			Hardness in HB	250 max.
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 S 32050	ASTM	USA	Plate, Sheet and Strip
A358 S 32050	ASTM	USA	Pipes
A959 S 32050	ASTM	USA	Plate, Sheet and Strip
A249 S 32050	ASTM	USA	Tubes for Superheater and Heat exchanger
A213 S 32050	ASTM	USA	Tubes for Superheater and Heat exchanger
A743 CK35MN	ASTM	USA	Casting
S 32050	UNS	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com